

1. DESCRIPTION

Weldable steel wire rod in coils for drawing according to ISO 16120-2 C20D.
Chemical composition suitable for galvanizing.

2. HEAT CHEMICAL COMPOSITION

	C %	Mn %	Si %	P %	S %	Mn/Si
min	0.18	0.45	0.15	-	-	2.7
max	0.23	0.55	0.20	0.020	0.025	-

Permissible deviations of product analysis according to ISO16120-2.

3. MECHANICAL AND DIMENSIONAL PROPERTIES

Tensile strength: $480 \leq R_m \text{ [MPa]} \leq 540$

Elongation: $A_{10} \text{ [%]} \geq 25$

$Z \geq 55\%$

Diameter range: 5,5 – 21,5 mm

Diameter tolerance and out-of-round: according to ISO 16124 grade T2.

Diameter [mm]	5,5 ÷ 10	11 ÷ 15	16 ÷ 21,5
Tolerance [mm]	±0,25	±0,30	±0,35
Out-of-round max [mm]	0,40	0,48	0,56

Any geometric defect regarding the tail of the coils could occur within a distance from the end of wire rod greater than those included in ISO 16124 Table 11.

4. SURFACE AND INTERNAL QUALITY

Surface quality: according to ISO 16120-2 par. 4.3 and 4.4 – maximum defect depth 0,20 mm.

Internal quality: absence of defects compromising use (ISO 16120-2 par. 4.5).

5. STANDARD PACKING

In coils up to approx. 2500 kg, inside diameter about 800 mm, outside diameter about 1200 mm, maximum length 1900 mm.

6. STANDARD IDENTIFICATION

Each coil with label reporting: Heat number, nominal diameter, steel quality (grade), weight and date of rolling. Additional colored label to distinguish different heats.

7. STANDARD CERTIFICATION

On demand Inspection Certificate according to EN 10204 3.1.

